

CSF-347(P)

For 18%Cr-8%Ni-Cb Stainless steel

AWS	A5.22	E347T0(1)-1/-4
KS	D 3612	YF347C
JIS	Z3323	TS347-FB0(1)

Applications

CSF-347(P) is suitable for Welding of low carbon 18%Cr-8%Ni-Cb Stainless steel (SUS347), 18%Cr-8%Ni-Ti Stainless steel.

Characteristics

- (1) CSF-347(P) is flux cored wire and designed for Fillet & H-F(All-position) welding with CO₂ gas Shielding.
- (2) It provides the excellent usability with stable arc, less spattering, good bead appearance, better slag removal, and less quantity of welding fume comparable to solid wire.
- (3) Is containing Ferrite of a reasonable quantity and crack-resistance, intergranular corrosion resistance, mechanical properties of weld metal is superior.
- (4) Shield gas is 100%CO₂ or Ar+CO₂ gas.

Notes on usage

- (1) The optimum flow of CO₂ for Shielding is 20~25 ℓ /min.
- (2) Protect the weld with a screen to prevent blowholes caused by wind where the wind velocity is 2m/sec and more.
- (3) Keep the distance between tip & base metal at 15~25mm.

Typical chemical composition of weld metal (%)

(Shielding Gas : 100%CO₂)

	C	Mn	Si	P	S	Cr	Ni	Cb	FN
CSF-347	0.030	1.40	0.55	0.015	0.010	19.6	10.0	0.41	8.7
CSF-347P	0.028	1.40	0.50	0.012	0.009	19.5	10.01	0.45	9.0

Typical mechanical properties of weld metal

(Shielding Gas : 100%CO₂)

	YP N/mm ² (MPa)	TS N/mm ² (MPa)	EL %	IV (J)
				0℃
CSF-347	486	665	38.0	55
CSF-347P	474	624	38.0	58

Size & recommended current range (DC +)

Dia. mm (in)	Current(A)	Voltage(V)	Welding Speed(cm /min)
1.2(0.045)	150~300	24~33	20~60
1.6(0.062)	200~400	24~33	20~60